

### AMENDMENTS TO THE CLAIMS

The following Listing of Claims replaces all previous listings of claims in the application.

#### Listing of Claims:

1. (Previously presented) A process for producing a catalyst for gas-phase oxidations, the process comprising: applying a suspension of  $\text{TiO}_2$  and  $\text{V}_2\text{O}_5$  particles to a fluidized inert support, wherein at least 90% by volume of the  $\text{V}_2\text{O}_5$  particles have a diameter of 20  $\mu\text{m}$  or less and at least 95% by volume of the  $\text{V}_2\text{O}_5$  particles have a diameter of 30  $\mu\text{m}$  or less.
2. (Original) The process according to claim 1, wherein at least 90% by volume of the  $\text{V}_2\text{O}_5$  particles have a diameter of 15  $\mu\text{m}$  or less and at least 95% by volume of the  $\text{V}_2\text{O}_5$  particles have a diameter of 20  $\mu\text{m}$  or less.
3. (Previously presented) The process according to claim 1, wherein at least 50% by volume of the  $\text{V}_2\text{O}_5$  particles have a diameter of more than 2  $\mu\text{m}$ .
4. (Previously presented) The process according to claim 1, wherein the suspension further comprises one or more elements selected from the group consisting of cesium, phosphorus and antimony source.
5. (Currently amended) The process according to claim 1, wherein the catalyst includes a catalytically active composition ~~comprises~~ comprising from 1 to 40% by weight of vanadium oxide, calculated as  $\text{V}_2\text{O}_5$ , and from 60 to 99% by weight of titanium dioxide, calculated as  $\text{TiO}_2$ .
6. (Currently amended) The process according to claim 5, wherein the catalyst includes a catalytically active composition further ~~comprises~~ comprising, based on the total amount of catalytically active composition, up to 1% by weight of a cesium compound, calculated as Cs, up to 1% by weight of a phosphorus compound, calculated as P, and up to 10% by weight of antimony oxide, calculated as  $\text{Sb}_2\text{O}_3$ .

7. (Previously presented) The process according to claim 2, wherein at least 50% by volume of the  $V_2O_5$  particles have a diameter of more than 2  $\mu m$ .

8. (Previously presented) The process according to claim 2, wherein the suspension further comprises one or more elements selected from cesium, phosphorus and antimony source.

9. (Currently amended) The process according to claim 2, wherein the catalyst includes a catalytically active composition ~~comprises comprising~~ from 1 to 40% by weight of vanadium oxide, calculated as  $V_2O_5$ , and from 60 to 99% by weight of titanium dioxide, calculated as  $TiO_2$ .

10. (Currently amended) The process according to claim 4, wherein the catalyst includes a catalytically active composition ~~comprises comprising~~ from 1 to 40% by weight of vanadium oxide, calculated as  $V_2O_5$ , and from 60 to 99% by weight of titanium dioxide, calculated as  $TiO_2$ .

11. (Previously presented) The process according to claim 1, wherein the suspension further comprises a cesium compound, a phosphorus compound and antimony oxide.

12. (Previously presented) The process according to claim 11, wherein the catalyst includes a catalytically active composition comprising:

1-40% by weight of vanadium oxide, calculated as  $V_2O_5$ , and from 60 to 99% by weight of titanium dioxide, calculated as  $TiO_2$ ;

up to 1% by weight of a cesium compound, calculated as Cs, up to 1% by weight of a phosphorus compound, calculated as P; and

up to 10% by weight of antimony oxide, calculated as  $Sb_2O_3$ .

13. (Previously presented) A catalyst prepared by a process comprising:

providing a suspension of  $\text{TiO}_2$  and  $\text{V}_2\text{O}_5$  particles, wherein at least 90% by volume of the  $\text{V}_2\text{O}_5$  particles have a diameter of 20  $\mu\text{m}$  or less and at least 95% by volume of the  $\text{V}_2\text{O}_5$  particles have a diameter of 30  $\mu\text{m}$  or less;

and providing a fluidized support in a stream of flowing gas, and contacting the fluidized support with the suspension of  $\text{TiO}_2$  and  $\text{V}_2\text{O}_5$  particles to provide a supported catalyst, wherein the supported catalyst further comprises up to 1% by weight of a cesium compound, calculated as Cs, up to 1% by weight of a phosphorus compound, calculated as P, and up to 10% by weight of antimony oxide, calculated as  $\text{Sb}_2\text{O}_3$ , based on the total weight percent catalyst.

14. (Currently amended) The catalyst according to claim 13, further comprising an outer layer with an  $\text{Sb}_2\text{O}_3$  content by weight that is 50% to 100% lower than the  $\text{Sb}_2\text{O}_3$  content by weight of an inner layer of the supported catalyst.

15. (Currently amended) The catalyst according to ~~claim 1~~, claim 13, wherein the flowing gas is at a temperature of from 60°C to 150°C.